

JAPIO

(c) 2006 JPO & JAPIO. All rights reserved.

03231514 **MAKEUP COMPOSITION AND PRODUCTION THEREOF**

Pub. No.: 02-207014 [**JP 2207014 A**]

Published: August 16, 1990 (19900816)

Inventor: KUZUMOTO HIROYOSHI

IZEKI SEIJI

MATSUI TOSHITAKA

KIDA YOSHIE

Applicant: OKAMURA SEIYU KK [358705] (A Japanese Company or Corporation), JP (Japan)

Application No.: 01-028456 [JP 8928456]

Filed: February 06, 1989 (19890206)

International Class: [5] A61K-007/02

JAPIO Class: 14.4 (ORGANIC CHEMISTRY -- Medicine); 13.2 (INORGANIC CHEMISTRY -- Inorganic Compounds)

Journal: Section: C, Section No. 774, Vol. 14, No. 497, Pg. 94, October 30, 1990 (19901030)

ABSTRACT

PURPOSE: To obtain a makeup composition, excellent in dispersibility and good in feeling of use and further transparency and capable of giving more aesthetic makeup without causing precipitation or flocculation, discoloration and deterioration by blending a cosmetic base with ultrafine particulate magnetite having a uniform particle diameter.

CONSTITUTION: A makeup composition obtained by blending 100 pts.wt. cosmetic base with 0.01-40 pts.wt. ultrafine particulate magnetite containing ≥ 92.5 wt.% ultrafine particles having a particle diameter within the range of 50-350 angstroms as a transparent iron oxide-based pigment. The above-mentioned ultrafine particulate magnetite is prepared by adding a basic solution to an aqueous solution containing a soluble ferrous salt and a soluble ferric salt, forming a sol of a positive transparent hydrated iron oxide having ≤ 300 angstroms average particle diameter within an acidic region, aging and stabilizing the sol at \geq ambient temperature, then adding a surfactant, flocculating the sol, subsequently adding an organic dispersion, passing the afore-mentioned sol into an organic layer, separating the organic layer, adding water thereto, adding a basic aqueous solution thereto while heating and stirring the mixture at ≥ 50 deg.C and regulating the pH to ≥ 9 .